

**PRODUCT DATA SHEET****EMPEYOL F3502****DESCRIPTION**

EMPEYOL F3502 is a modified 3500 molecular weight, trihydroxy polyether polyol. It is designed especially for the manufacture of one shot flexible urethane slabstock foams. The full range flexible foams from extra super soft to extra firm of varying densities can be made with this polyol. It is particularly useful in producing low density cushioning foams, high density automotive unfilled foams and high density filled foams for furniture. It produces foams with exceptionally high breath abilities which remain so over a wide range of tin catalyst levels. It affords excellent tin catalyst latitudes.

**SALES SPECIFICATION**

Characteristics	Unit	Specification
Appearance	----	Clear viscous liquid
Density at 25 °C	g/cc	1.005 – 1.015
Viscosity at 25 °C	Cps	600± 100
Colour	APHA	100 maximum
Hydroxyl Number	mgKOH/g	46.0 – 48.0
Water	% w/w	0.10 maximum
Foam test	----	To pass the test

**PACKING SIZE** : 208 / 25 kg nett.

**STORAGE AND HANDLING**

- EMPEYOL F3502 polyol is to be stored in tightly closed containers preferably at temperatures between 20 –35 °C.
- Should wear gloves and goggles during handling.
- Shelf life : 1 year

**HEALTH AND SAFETY ADVICE**

EMPEYOL F3502 polyol should present no unusual health problems when used in manufacturing operations where satisfactory standards of personal and industrial hygiene are maintained. Precautions should be taken to avoid exposure to the eye or prolonged contact with the skin.

---

The information in this data sheet is believed to be accurate but all recommendations are made without warranty, since the conditions of use are beyond the company's control. MPL disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of any of its products in combination with other materials or in any process.

---